Lapping the Micro-Fine Ceramics
Posted by wickededge - 19 Jul 2012 19:08

Cliff Stamp has posted elsewhere that these stones definitely benefit from lapping. Today I worked on my set and it made a huge difference. You can easily use the diamond stones in your set to lap your ceramics and depending on which grit you use to finish, you can dramatically alter the way the stone performs. My coarse Micro-Fine stones were more coarse than I wanted at the moment, so I took them all the way up to the 1000# diamonds, progressing from the 100# stones up the line. I also have a 3um diamond bench stone that I used to finish and the coarse Micro-Fines were like a whole different set of stones. I can see where there might be times when I want to add a little texture back to them to give certain knives a little bite, so I'll experiment with lapping on different grit stones and see what comes of it.

==========

Re: Lapping the Micro-Fine Ceramics
Posted by RalphHoneycutt - 19 Jul 2012 20:38

Clay, This is very helpful. I did not really notice the aggressiveness of the mirco-fine ceramics. I will try it with the higher grit diamond stones. I am very satisfied with the micro-fine ceramics. For my purposes they produce excellent results. If the micro-fine ceramics had been available 6 months ago, I may not have been so determined to buy the Choseras and Shaptons, but I like them all for different reasons. The micro-fine ceramics are the best value (IMO).

Ralph

==========

Re: Lapping the Micro-Fine Ceramics
Posted by StevenCorpstein - 20 Jul 2012 00:21

Ralph,

  So are you going from the 1000 grit diamonds to the micro-fine ceramic paddles, or are you using something between them first?

==========

Re: Lapping the Micro-Fine Ceramics
Posted by cbwx34 - 20 Jul 2012 07:21

---

wickededge wrote:

My coarse Micro-Fine stones were more coarse than I wanted at the moment, so I took them all the way

up to the 1000# diamonds, progressing from the 100# stones up the line. I also have a 3um diamond bench stone that I used to finish and the coarse Micro-Fines were like a whole different set of stones.

Was just wondering why the lapping progression vs. just lapping on just the finer stone,,, or maybe just the 1000 & 3um?

How much time on each stone did you spend? I'm guessing this doesn't take much?

Any idea how much of the ceramic (thickness) this used?

Thanks!

cbw

==========

Re: Lapping the Micro-Fine Ceramics

Posted by RalphHoneycutt - 20 Jul 2012 07:49

_____

Steven, After the 1000 grit diamond stone, I use the super-fine ceramics and then the micro-fine. I have not yet tried going directly to the micro-fine ceramics from the 1000 grit. I will give it a try this weekend.

Ralph

==========

Re: Lapping the Micro-Fine Ceramics

Posted by wickededge - 20 Jul 2012 08:50

_____

I started lapping with the 800 grit and it was going well but there were a couple high spots so I decided to knock those off with the coarse stones. I didn't measure before I started and now I wish I had, but I can't imagine I removed more the a couple thousandths judging from the material that came off.

cbwx34 wrote:

wickededge wrote:

My coarse Micro-Fine stones were more coarse than I wanted at the moment, so I took them all the way up to the 1000# diamonds, progressing from the 100# stones up the line. I also have a 3um diamond bench stone that I used to finish and the coarse Micro-Fines were like a whole different set of stones.

Was just wondering why the lapping progression vs. just lapping on just the finer stone,,, or maybe just the 1000 & 3um?

How much time on each stone did you spend? I'm guessing this doesn't take much?

Any idea how much of the ceramic (thickness) this used?

Thanks!

cbw

==========

Re: Lapping the Micro-Fine Ceramics

Posted by cbwx34 - 24 Jul 2012 09:45

_____

I wanted to do a couple more knives before I posted this. I could tell the coarse Micro-fine was more coarse than rated... but as an alternative to lapping, I've been using it after the 1000g diamond, which seems to set up the edge better for the rest of the ceramics. So. I'll go Coarse Micro-fine. --> 1200 --> 1600 ceramics --> Fine Micro-fine... then onto leather (if desired).

Just thought I'd present an alternate use that I'm liking.

==========

Re: Lapping the Micro-Fine Ceramics

Posted by wickededge - 24 Jul 2012 10:18

_____

That's exactly what I was doing before I lapped my coarse Micro-fine stones and it worked great. Now that they're all smoothed out, I'll have to see if it still works well in that progression.

cbwx34 wrote:

I wanted to do a couple more knives before I posted this. I could tell the coarse Micro-fine was more coarse than rated... but as an alternative to lapping, I've been using it after the 1000g diamond, which seems to set up the edge better for the rest of the ceramics. So. I'll go Coarse Micro-fine. --> 1200 --> 1600 ceramics --> Fine Micro-fine... then onto leather (if desired).

Just thought I'd present an alternate use that I'm liking.

==========

Re: Lapping the Micro-Fine Ceramics

Posted by ScottSherman - 25 Aug 2012 15:10

_____

what is "um" and how does it relate to grit numbers? I.E. how many um's to a grit or a 100 grit for example or perhaps vice versa? What grit would a stone be to equal a "um" or a fixed quantity of "um's"?

Thanks.

Scott

==========

Re: Lapping the Micro-Fine Ceramics

Posted by wickededge - 25 Aug 2012 19:56

_____

Good question Scott. um is the abbreviation for Micron. Here is a chart that shows how they all compare: Grit Comparison Chart

ScottSherman wrote:

what is "um" and how does it relate to grit numbers? I.E. how many um's to a grit or a 100 grit for example or perhaps vice versa? What grit would a stone be to equal a "um" or a fixed quantity of "um's"?

Thanks.

Scott

==========